

Amendments to the Abstract:

Kindly replace the Abstract, as filed in the present application, with the following amended Abstract:

~~The present invention provides a Ni-Pt alloy superior in workability containing Pt in a content of 0.1 to 20 wt% Pt and having a Vickers hardness of 40 to 90, and a target comprising the Ni-Pt alloy are provided. The present invention also provides a A manufacturing method of Ni-Pt alloy superior in workability comprising includes a step of~~ subjecting a raw material Ni having a 3N purity of 3N level to electrochemical dissolution, ~~a step of~~ neutralizing the electrolytically leached solution with ammonia, ~~a step of~~ removing impurities through filtration with activated carbon, ~~a step of~~ blowing carbon dioxide into the resultant solution to form nickel carbonate and exposing the resultant product to a reducing atmosphere to prepare high purity Ni powder, ~~a step of~~ leaching a raw material Pt having a 3N purity of 3N level with acid, ~~a step of~~ subjecting the leached solution to electrolysis to prepare high purity electrodeposited Pt, and ~~a step of~~ dissolving the resultant high purity Ni powder and high purity electrodeposited Pt. The foregoing method enables the rolling of the Ni-Pt alloy ingot upon reducing the hardness thereof, which results in the stable and efficient manufacture of a rolled target.